

**Client:** Mid Ocean Brands B.V.

**Address:** Unit 711 - 716, 7/F., Tower A, 83 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong

**The following merchandise was (were) submitted and identified by the client as:**

**Name of Product:** 9 stone ice cubes in box

**Model No.:** MO9942

**Supplier:** 103225

**Sample Received:** Sep. 12, 2025

Sep. 26, 2025

**Test Period:** Sep. 12, 2025 - Sep. 24, 2025

Sep. 26, 2025 - Sep. 26, 2025

**This report replaces the original report and is numbered JTS25097523-1ER1.**

**Overall Result :** PASS

**Test specification :** Please refer to next page.

**Prepared by :** 

Luna Zhao

Report editor

**Reviewed By :** 

Sigrid Shentu

Quality Manager

**Issued By :** 

Carl Zhu

Authorized Signatory



NPS Survey



Verification Report

**Test Requested and Conclusion(s):**

No.	Test Requested	Conclusion(s)
1	Technical Guide on Council of Europe Resolution CM/Res(2020)9, Technical Guide on Metals and Alloys used in food contact materials and articles of the 2nd edition in 2024, General Requirement (Article 3) in EU Regulation (EC) No 1935/2004	
1-1	-Extractable Heavy Metals for Metal	<b>PASS</b>
2	As requested by the client, according to European Council Directive 84/500/EEC and its amendment 2005/31/EC - Amending Council Directive 84/500/EEC as regards a declaration of compliance and performance criteria of the analytical method for ceramic articles intended to come into contact with foodstuffs, General Requirement (Article 3) in EU Regulation No. 1935/2004	
2-1	-Release of Lead and Cadmium	<b>PASS</b>
3	1907/2006 REACH Annex XVII Item 63 - Total Lead (Pb)	<b>PASS</b>
4	1907/2006 REACH Annex XVII Item 23 - Total Cadmium (Cd)	<b>PASS</b>
5	1907/2006 REACH Annex XVII Item 51&52 - Phthalates	<b>PASS</b>
6	1907/2006 REACH Annex XVII Item 43 - AZO	<b>PASS</b>
7	1907/2006 REACH Annex XVII Item 50 - Polycyclic Aromatic Hydrocarbons (PAHs) content	<b>PASS</b>
8	Regulation (EU) 2019/1021 of the European Parliament and of the Council of 20 June 2019 on persistent organic pollutants and its subsequent amendments Directive. - Pentachlorophenol (PCP) content	<b>PASS</b>
9	-Colour fastness to rubbing-Client's limit	<b>PASS</b>
10	BS EN 12875-1:2005 Mechanical dishwashing resistance of utensils – Part 1: Reference test method for domestic articles	<b>PASS</b>
11	Entry 77 of Regulation (EU) 2023/1464 amending Annex XVII of REACH Regulation (EC) No 1907/2006 -Formaldehyde Release	<b>PASS</b>

\*\*\* To be continued \*\*\*

**Test Result(s):**

**1-1.Extractable Heavy Metals**

Method: with reference to Technical Guide on Metals and Alloys used in food contact materials and articles of the 2nd edition in 2024 and by Inductively Coupled Plasma Mass Spectrometry (ICP-MS).

Material No.	5					
Extractable Elements	The 1 <sup>st</sup> Result(mg/kg)	The 2 <sup>nd</sup> Result (mg/kg)	The 1 <sup>st</sup> + 2 <sup>nd</sup> Result (mg/kg)	7*Limit (mg/kg)	The 3 <sup>rd</sup> Result(mg/kg)	Limit (mg/kg)
Silver(Ag)	N.D.	N.D.	N.D.	0.56	N.D.	0.08
Aluminium (Al)	N.D.	N.D.	N.D.	35	N.D.	5
Chromium(Cr)	N.D.	N.D.	N.D.	7	N.D.	1
Cobalt (Co)	N.D.	N.D.	N.D.	0.14	N.D.	0.02
Copper(Cu)	N.D.	N.D.	N.D.	28	N.D.	4
Iron(Fe)	2.4	0.3	2.7	280	0.2	40
Magnesium (Mg)	N.D.	N.D.	N.D.	--	N.D.	--
Manganese (Mn)	N.D.	N.D.	0.2	3.85	N.D.	0.55
Molybdenum(Mo)	N.D.	0.003	0.003	0.84	N.D.	0.12
Nickel (Ni)	N.D.	N.D.	N.D.	0.98	N.D.	0.14
Tin (Sn)	N.D.	0.3	0.3	700	N.D.	100
Titanium(Ti)	N.D.	N.D.	N.D.	--	N.D.	--
Vanadium(V)	N.D.	N.D.	N.D.	0.07	N.D.	0.01
Zinc(Zn)	N.D.	N.D.	N.D.	35	N.D.	5
Antimony(Sb)	N.D.	N.D.	N.D.	0.28	N.D.	0.04
Arsenic (As)	N.D.	0.0002	0.0002	0.014	N.D.	0.002
Barium(Ba)	N.D.	N.D.	N.D.	8.4	N.D.	1.2
Beryllium (Be)	N.D.	N.D.	N.D.	0.07	N.D.	0.01
Cadmium(Cd)	N.D.	N.D.	N.D.	0.035	N.D.	0.005
Lead(Pb)	0.002	0.002	0.004	0.07	0.002	0.01
Lithium (Li)	N.D.	N.D.	N.D.	0.336	N.D.	0.048
Mercury (Hg)	N.D.	N.D.	N.D.	0.021	N.D.	0.003
Thallium (Tl)	N.D.	N.D.	N.D.	0.007	N.D.	0.001
Zirconium (Zr)	N.D.	N.D.	N.D.	14	N.D.	2
Conclusion	PASS					

- Note:**
1. mg/kg = milligram per kilogram (ppm).
  2. MDL= Method detection limit.
  3. N.D. = Not detected, less than MDL.
  4. Test condition: 70 °C,2 hours with Artificial tap Citric Acid.
  5. The submitted sample/component is a repeated use article. The migration test was carried out three times on the same article. The sum of the results of the first and second tests should not exceed seven times the limit (Result 1<sup>st</sup> test + Result 2<sup>nd</sup> test <7\* limit) and the Result 3<sup>rd</sup> should not exceed the limit.

## 2-1. Release of Lead and Cadmium

Method: With reference to EN 1388-2: 1995, analyzed by Atomic Absorption Spectroscopy (AAS).

Material No.	Test Item	4% Acetic Volume/article	Result (mg/L)				Conclusion
			1	2	3	4	
4	Lead(Pb)	167	<0.1	<0.1	<0.1	<0.1	PASS
	Cadmium(Cd)		<0.01	<0.01	<0.01	<0.01	PASS

**Note:** 1. Sample preparation in 4% Acetic acid at 22°C for 24 hours.

Permissible limit of 84/500/EEC&2005/31/EC

Utensil shape	Lead	Cadmium
Flatware depth 25 mm	0.8 mg/dm <sup>2</sup>	0.07 mg/dm <sup>2</sup>
Other appliances that can be filled	4 mg/l	0.3 mg/l
Kitchenware/packaging/storage with volume >3L	1.5 mg/l	0.1 mg/l

\*\*\* To be continued \*\*\*

### 3.Total Lead (Pb)

Method: With reference to CPSC-CH-E1001-08.3, analyzed by Atomic Absorption Spectroscopy (AAS)

Material No.	Limit (mg/kg)	Result (mg/kg)	Conclusion
5	500	34	PASS
6+7+8*	500	27	PASS

### 3.Total Lead (Pb)

Method: With reference to CPSC-CH-E1002-08.3, analyzed by Atomic Absorption Spectroscopy (AAS)

Material No.	Limit (mg/kg)	Result (mg/kg)	Conclusion
1	500	N.D.	PASS
2+3*	500	N.D.	PASS
4	500	N.D.	PASS

### 3.Total Lead (Pb)

Method: With reference to CPSC-CH-E1003-09.1, analyzed by Atomic Absorption Spectroscopy (AAS)

Material No.	Limit (mg/kg)	Result (mg/kg)	Conclusion
9	500	15	PASS
10	500	N.D.	PASS

- Note:**
1. mg/kg = milligram per kilogram (ppm).
  2. MDL (Method detection limit) = 10 mg/kg.
  3. N.D. = Not detected, less than MDL.
  4. "\*" According to the customer's requirements, the samples were mixed tested. The test result is the overall result of mixed samples. And may be different from any single test result.
  5. The data of point 1 is derived from the report numbered point 2 of JTS25090259-1ER2.
  6. The data of point 10 is derived from the report numbered point 12 of JTS25090259-1ER2.

\*\*\* To be continued \*\*\*

#### 4.Total Cadmium (Cd)

Method: With reference to CPSC-CH-E1001-08.3, analyzed by Atomic Absorption Spectroscopy (AAS)

Material No.	Limit (mg/kg)	Result (mg/kg)	Conclusion
5	100	N.D.	PASS
6+7+8*	100	N.D.	PASS

#### 4.Total Cadmium (Cd)

Method: With reference to CPSC-CH-E1002-08.3, analyzed by Atomic Absorption Spectroscopy (AAS)

Material No.	Limit (mg/kg)	Result (mg/kg)	Conclusion
2+3*	100	N.D.	PASS
4	100	N.D.	PASS

#### 4.Total Cadmium (Cd)

Method: With reference to CPSC-CH-E1003-09.1, analyzed by Atomic Absorption Spectroscopy (AAS)

Material No.	Limit (mg/kg)	Result (mg/kg)	Conclusion
9	1000	N.D.	PASS
10	1000	N.D.	PASS

- Note:**
1. mg/kg = milligram per kilogram (ppm).
  2. MDL (Method detection limit) = 10 mg/kg.
  3. N.D. = Not detected, less than MDL.
  4. "\*" According to the customer's requirements, the samples were mixed tested. The test result is the overall result of mixed samples. And may be different from any single test result.
  5. The data of point 10 is derived from the report numbered point 12 of JTS25090259-1ER2.

\*\*\* To be continued \*\*\*

## 5. Phthalates

Method: With reference to EN ISO 14389:2022, analyzed by Gas Chromatograph-Mass Spectrometer (GC-MS).

Substances	CAS No.	MDL(%)	Limit (%)	Result (%)	
				9	10
DIBP	84-69-5	0.005	--	N.D.	N.D.
DBP	84-74-2	0.005	--	N.D.	0.008
DEHP	117-81-7	0.005	--	N.D.	N.D.
BBP	85-68-7	0.005	--	N.D.	N.D.
SUM	--	--	<0.1	<0.1	0.008
DNOP	117-84-0	0.005	--	N.D.	N.D.
DINP	28553-12-0 /68515-48-0	0.010	--	N.D.	N.D.
DIDP	26761-40-0 /68515-49-1	0.010	--	N.D.	N.D.
SUM	--	--	<0.1	<0.1	<0.1
Conclusion				PASS	PASS

- Note:**
1. MDL = Method detection limit.
  2. N.D. = Not detected, less than MDL.
  3. The data of point 10 is derived from the report numbered point 12 of JTS25090259-1ER2.

\*\*\*To be continued\*\*\*

## 6.AZO Contents

Method: With reference to EN ISO 14362-1:2017, analyzed by Gas Chromatograph-Mass Spectrometry (GC-MS).

No.	Substances Name	CAS No.	Limit (mg/kg)	Result (mg/kg)
				2+3*
1	biphenyl-4-ylamine/ 4-aminodiphenyl/ xenylamine	92-67-1	30	N.D.
2	benzidine	92-87-5	30	N.D.
3	4-chloro-o-toluidine	95-69-2	30	N.D.
4	2-naphthylamine	91-59-8	30	N.D.
5	o-aminoazotoluene/ 4-o-tolylazo-o-toluidine/ 4-amino-2', 3-dimethylazobenzene	97-56-3	30	N.D.
6	2-amino-4-nitrotoluene/ 5-nitro-o-toluidine	99-55-8	30	N.D.
7	4-chloroaniline	106-47-8	30	N.D.
8	4-methoxy-m-phenylenediamine	615-05-4	30	N.D.
9	4,4'-methylenedianiline/ 4,4'- diaminodiphenylmethane	101-77-9	30	N.D.
10	3,3'-dichlorobenzidine/ 3,3'-dichlorobiphenyl-4,4'- ylenediamine	91-94-1	30	N.D.
11	3,3'-dimethoxybenzidine/ o-dianisidine	119-90-4	30	N.D.
12	3,3'-dimethylbenzidine/ 4,4'-bi-o-toluidine	119-93-7	30	N.D.
13	4,4'-methylenedi-o-toluidine	838-88-0	30	N.D.
14	6-methoxy-m-toluidine/ p-cresidine	120-71-8	30	N.D.
15	4,4'-methylene-bis-(2-chloroaniline)/ 2,2'-dichloro- 4,4'-methylene-dianiline	101-14-4	30	N.D.
16	4,4'-oxydianiline	101-80-4	30	N.D.
17	4,4'-thiodianiline	139-65-1	30	N.D.
18	o-toluidine/ 2-aminotoluene	95-53-4	30	N.D.
19	4-methyl-m-phenylenediamine/ 2,4-toluylendiamine	95-80-7	30	N.D.
20	2,4,5-trimethylaniline	137-17-7	30	N.D.
21	o-anisidine / 2-methoxyaniline	90-04-0	30	N.D.
22	4-aminoazobenzene	60-09-3	30	N.D.
Conclusion				PASS

- Note:**
1. mg/kg = milligram per kilogram (ppm).
  2. MDL (Method detection limit) = 10 mg/kg.
  3. N.D. = Not detected, less than MDL.
  4. "\*" According to the customer's requirements, the samples were mixed tested. The test result is the overall result of mixed samples. And may be different from any single test result

## 7.Polycyclic Aromatic Hydrocarbons (PAHs)

Method: With reference to AfPS GS 2019:01 PAK, analyzed by Gas Chromatograph-Mass Spectrometry (GC-MS).

Test Substance	CAS No.	Limit (mg/kg)	Result (mg/kg)
		II	9
Benzo[a]anthracene(BaA)	56-55-3	1	N.D.
Chrysene (CHR)	218-01-9	1	N.D.
Benzo[b]fluoranthene(BbF)	205-99-2	1	N.D.
Benzo[k]fluoranthene(BkF)	207-08-9	1	N.D.
Benzo[a]pyrene(BaP)	50-32-8	1	N.D.
Dibenzo[a,h]anthracene(DBA)	53-70-3	1	N.D.
Benzo[e]pyrene(BeP)	192-97-2	1	N.D.
Benzo[j]fluoranthene(BjF)	205-82-3	1	N.D.
<b>SUM</b>		10	--
Conclusion			PASS

Test Substance	CAS No.	Limit (mg/kg)	Result (mg/kg)
		II	10
Benzo[a]anthracene(BaA)	56-55-3	1	N.D.
Chrysene (CHR)	218-01-9	1	N.D.
Benzo[b]fluoranthene(BbF)	205-99-2	1	N.D.
Benzo[k]fluoranthene(BkF)	207-08-9	1	N.D.
Benzo[a]pyrene(BaP)	50-32-8	1	N.D.
Dibenzo[a,h]anthracene(DBA)	53-70-3	1	N.D.
Benzo[e]pyrene(BeP)	192-97-2	1	N.D.
Benzo[j]fluoranthene(BjF)	205-82-3	1	N.D.
<b>SUM</b>		10	--
Conclusion			PASS

\*\*\*To be continued\*\*\*

- Note:**
1. mg/kg = milligram per kilogram (ppm).
  2. MDL (Method detection limit) = 0.20 mg/kg.
  3. N.D. = Not detected, less than MDL.
  4. "--" = Not Regulated.
  5. Product Class:
    - I = Extender oils.
    - II = Rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity, under normal or reasonably foreseeable conditions of use.
    - III = Toys, including activity toys, and childcare articles, if any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity, under normal or reasonably foreseeable conditions of use.
  6. The data of point 10 is derived from the report numbered point 12 of JTS25090259-1ER2.

**\*\*\*To be continued\*\*\***

### 8.Pentachlorophenol (PCP) Content

Method: With reference to ISO 15320:2001, analysis was performed by GC-MS.

Test Item	MDL(mg/kg)	Test Results(mg/kg)	Limited Value(mg/kg)	Conclusion
		1		
Pentachlorophenol (PCP)	0.1	N.D.	5	PASS

- Note:
1. mg/kg = milligram per kilogram (ppm).
  2. MDL = Method detection limit.
  3. N.D. = Not detected, less than MDL.
  4. The data of point 1 is derived from the report numbered point 2 of JTS25090259-1ER2.

### 9.Colour fastness to rubbing(Unit:Grade)

Method: ISO 105-X16:2016

Sample	Requirement	Result		Conclusion
		Dry	Wet	
2	Dry≥3.0	4.5	3.5	PASS
	Wet≥3.0			

**Note:**

Explanation of colorfastness results:

- Grade 5 negligible or no changing or staining
- Grade 4 slightly changing or staining
- Grade 3 noticeably changing or staining
- Grade 2 considerably changing or staining
- Grade 1 much changing or heavily staining

\*\*\*To be continued\*\*\*

**10.BS EN 12875-1:2005 Mechanical dishwashing resistance of utensils - Part 1: Reference test method for domestic articles (Whole Product)**

Method: BS EN 12875-1:2005 Mechanical dishwashing resistance of utensils — Part 1: Reference test method for domestic articles

1. Visually inspect samples and record any cosmetic defects
2. Load the dishwasher with tested samples. The other sample will be used as the standard.
3. Fill the dishwasher soap holder with the powder detergent, close and lock the dishwasher as recommended in the operating instructions.
4. Run the dishwasher for 10 cycles with 149°F(65°C) water at “normal setting” for housewares. Each cycle includes soaking, washing and drying
5. Remove and visually examine each sample

Test Requirement: The sample shall show no signs of discoloration or cracking after testing.

Sample size: 1 pieces

Test result: details show as following table:

Washing Cycle Sample No.	1 <sup>st</sup>	2 <sup>nd</sup>	3 <sup>rd</sup>	4 <sup>th</sup>	5 <sup>th</sup>	6 <sup>th</sup>	7 <sup>th</sup>	8 <sup>th</sup>	9 <sup>th</sup>	10 <sup>th</sup>
5	P	P	P	P	P	P	P	P	P	P

\*\*\*To be continued\*\*\*

**11.Entry 77 of Regulation(EU)2023/1464 amending Annex XVII of REACH Regulation(EC)No 1907/2006-Formaldehyde Release**

Method:With reference to EN717-1:2004 and Regulation (EU)2023/1464 Appendix 14,paragraph 1,analysis was performed by UV-Vis.

Test Item(s)	Limit	Unit(s)	MDL	1
Test chamber parameters				
Chamber Volume	-	m <sup>3</sup>	-	1.00
Testing climate-Temperature	-	°C	-	23.0
Testing climate-Relative Humidity	-	%	-	45
Ventilation (Air Change Rate)	-	/h	-	1.0
Sample Loading factor	-	m <sup>2</sup> /m <sup>3</sup>	-	1.000
Sampling Flow Rate	-	L/min	-	2.0
Sampling Time	-	min	-	60
Sampling Volume	-	L	-	120
Test result				
Formaldehyde Release(In air)	0.062	mg/m <sup>3</sup>	0.050	ND
Conclusion				PASS

**Notes:**

(1)At 23°C and 1013 hPa,the following relationship exists for formaldehyde:

1 ppm(parts per million)=1.24 mg/m<sup>3</sup>

1 mg/m<sup>3</sup>=0.81 ppm(parts per million)

(2)Reference Limit:

**Regulation(EU)2023/1464 of July 14,2023,amending Annex XVII of REACH as regards formaldehyde and formaldehyde releasers,Official Journal of the EU,July 17,2023**

Scope	Requirement	Method	Effective Date
Furniture and wood-based articles	≤0.062 mg/m <sup>3</sup>	Chamber method as described in Appendix 14,paragraph 1	After August 6,2026
Articles other than furniture and wood-based articles	≤0.080 mg/m <sup>3</sup>		
Interior of road vehicles, including trucks and buses	≤0.062 mg/m <sup>3</sup>	Ambient mode according to ISO 12219-1 or ISO 12219-10(see Appendix 14,paragraph 2)	After August 6,2027

Unless otherwise stated,the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule(w=0)stated in ILAC-G8:09/2019.


(3) The data of point 1 is derived from the report numbered point 2 of JTS25090259-1ER2.

Zhejiang J-testing Service Co.,Ltd.

**Test Material List:**

Material No.	Description	Location
1	Light brown bamboo	Box
2	Beige white fiber	Bag
3	Beige white fiber	Rope
4	Dark grey stone	Stone
5	Silvery metal	Clamp
6	Silvery metal	Substrate of screw
7	Silvery metal	Substrate of Iron Shard base
8	Silvery metal	Substrate of plectrum
9	Bronze coating	Coating of Iron Shard base
10	Clear varnish	Surface of bamboo

**Sample Photos**





25097523

\*\*\* End of Report \*\*\*





# TEST REPORT

Report No.: JTS25097523-1ER2

Date: Oct. 24, 2025

Page 16 of 16

## GENERAL CONDITIONS OF SERVICES

JTS Testing Services Co.,Ltd. (hereinafter "JTS"), while reserving the right to decline, without giving any reason whatsoever, any request for the undertaking of a test or investigation, will carry out at the request of the clients the required test or investigation subject always to the following conditions:

1. JTS only acts for the person or body originating the instructions (the "Clients"). No other party is entitled to give instructions, particularly on the scope of testing or delivery of report or certificate, unless authorized by the Clients.
2. The Sample(s) to be tested or investigated shall be delivered at the costs of the Clients and in accordance with the requirements of JTS. Improper shipping, packaging, and labeling of the Sample(s) by the Client may result in incorrect testing results, JTS shall be under no obligation to the Clients. At the conclusion of the test or investigation, the Clients shall, if required by JTS, collect the Sample(s). In any event, if the Sample(s) are not collected by the Clients within 30 days from the issuance date of the test report (for perishable items such as food and water samples, the relevant period shall be the preserving period up to 15 days), JTS may at its discretion dispose of the Sample(s) without any compensation to the Clients.
3. The Clients shall always comply with the following before or during JTS providing its services:
  - a) provide sample(s) and relevant data, at the same time, guarantee the consistence of the sample(s) name they declared with the sample(s) or the goods provided. Otherwise, JTS will not bear any relevant responsibilities;
  - b) giving timely instructions and adequate information to enable JTS to perform the services effectively;
  - c) supply, when requested by JTS, any equipment and personnel for the performance of the services;
  - d) take all necessary steps to eliminate or remedy any obstruction in the performance of the services;
  - e) inform JTS in advance of any hazards or dangers, actual or potential, associated with any order of samples or testing;
  - f) provide all necessary access for JTS's representative to enable the required services to be performed effectively;
  - g) ensure all essential steps are taken for safety of working conditions, sites and installations during the performance of services;
4. fully discharge all its liabilities under any contract like sales contract with a third party, whether or not a report or certificate has been issued by JTS, failing which JTS shall be under no obligation to the Clients.
4. Subject to JTS's accepting the Client's instructions, JTS will issue reports or certificates which reflect statements of opinion made with due care within the scope of instructions but JTS is not obliged to report upon any facts outside the instructions, if there were any dissidence about the report or certificate, the Client should provide the written declaration to JTS within 30 days after the date receiving the report or certificate, otherwise, JTS will not hear the case after the date limit.
5. JTS is irrevocably authorized by the Clients to deliver at its discretion the report or the certificate to any third party when instructed by the Clients or where it implicitly follows from circumstances, trade custom, usage or practice as determined by JTS.
6. A test report will be issued in confidence to the Clients and it will be strictly treated as such by JTS. It may not be reproduced either in its entirety or in part and it may not be used for advertising or other unauthorized purposes without the written consent of JTS. The Clients to whom the Report is issued may, however, show or send it, or a certified copy thereof prepared by JTS, to his customer, supplier or other persons directly concerned. JTS will not, without the consent of the Clients, enter into any discussion or correspondence with any third party concerning the contents of the report unless required by the relevant governmental authorities, laws or court orders.
7. Applicants wishing to use JTS's reports in court proceedings or arbitration shall inform JTS to that effect prior to submitting the sample for testing.
8. The report will refer only to the sample tested and will not apply to the bulk, unless the sampling has been carried out by JTS and is stated as such in the Report. Also, the report is only for reference.
9. Any documents containing engagements between the Clients and third parties like contracts of sale, letters of credit, bills of lading, etc. are regarded as information for JTS only and do not affect the scope of the services or the obligations accepted by JTS.
10. If the Clients do not specify the methods/standards to be applied, JTS will choose the appropriate ones and further information regarding the methods can be obtained by direct contact with JTS, for the in-house method, JTS will only provide the summary.
11. No liability shall be incurred by and no claim shall be made against JTS or its servants, agents, employees or independent contractors in respect of any loss or damage to any such materials, equipment and property occurring whilst at JTS or any work places in which the testing is carried out, or in the course of transit to or from JTS or the said work places, whether or not resulting from any acts, neglect or default on the part of any such servants, agents, employees or independent contractors of JTS.
12. JTS will not be liable, or accept responsibility for any loss or damage howsoever arising from the use of information contained in any of its reports or in any communication whatsoever about its said tests or investigations.
13. Subject to Clause 11 and 12, the total liability of JTS in respect of any claim of loss, damage or expense of whatsoever nature shall not exceed a total sum equal to two times the amount of the service fee payable in respect of the services directly related to such claim, and JTS's liability shall not include any indirect, special or consequential loss of the Clients.
14. In the event of JTS prevented by any cause outside JTS's control from performing any service for which an order has been given or an agreement made, the Clients shall pay to JTS:
  - a) the amount of all abortive expenditure actually made or incurred;
  - b) a proportion of the agreed fee or commission equal to the proportion (if any) of the service actually carried out by JTS, and JTS shall be relieved of all responsibility whatsoever for the partial or total non-performance of the required service.
15. JTS shall be discharged from all liabilities for all claims for loss, damage or expense unless suit is brought within one calendar year after the date of the performance by JTS of the service relating to the claim or in the event of any alleged non-performance within one year of the date when such service should have been completed.
16. The Clients acknowledge that JTS does not, either by entering into a contract or by performing service, assume or undertake to discharge any duty of the Clients to any other persons. JTS is neither an insurer nor a guarantor and disclaims all liability in such capacity.
17. The Clients shall hold harmless and indemnify JTS and its officers, employees, agents or independent contractors against all claims made by any third party for loss, damage or expense of whatsoever nature including reasonable legal expenses relating to the performance or non-performance of any services to the extent that the aggregate of any such claims relating to any one service exceed the limits mentioned in Clause 13.
18. Any unauthorized alteration, forgery or falsification of the content or appearance of the report/certificate is unlawful and offenders may be prosecuted to the fullest extent of the law; in the event of improper use of the report, JTS reserves the right to withdraw it, and to adopt any other measures which may be appropriate.
19. Samples are deposited with and accepted by JTS on the basis that either they are insured by the Clients or the Clients assumes entire responsibility for loss through fire, theft, burglary or for damages arising in the course of analysis or handling, without recourse whatsoever to JTS or its servants, agent, employees or independent contractors.
20. If the requirements of the Clients require the analysis of samples by the Clients' or any third party's laboratory, JTS will only convey the result of the analysis without responsibility for its accuracy. If JTS is only able to witness an analysis by the Clients' or any third party's laboratory JTS will only confirm that the correct sample has been analyzed without responsibility for the accuracy of any analysis or results.
21. In the event of any unforeseen additional time or costs being incurred in the course of carrying out any of its services, JTS shall be entitled to charge the Clients additional fees to reflect the additional time and costs incurred.
22. All rights (including but not limited to copyright) in any reports, certificates or other materials produced by JTS in the course of providing its services shall remain vested in JTS.
23. Unless otherwise agreed in writing, payment is to be made within 10 days from the date of Invoice or the date of the Debit Note, all charges rendered by JTS or interest will become due at the rate of three percent per month from the date of invoice until actual payment. The Clients are also responsible for settling all JTS's costs of collecting the charges owed, including legal fees.
24. Test results may be transmitted by electronic means at the Client's request. However, it should be noted that electronic transmission cannot guarantee the information contained will not be lost, delayed or intercepted by third party. JTS is not liable for any disclosure, error or omission in the content of such messages as a result of electronic transmission.
25. If necessary, JTS may subcontract part of or all tests to competent subcontractors. If no objection is raised at the time of the Clients submitting the application, JTS shall assume the Client's approval.
26. This report/certificate does not relieve sellers/suppliers from their contractual responsibility with regards to the quality/quantity of this delivery nor does it prejudice the Client's right to claim towards sellers/suppliers for compensation for any apparent and/or hidden defects not detected during JTS's random inspection or testing or audit.
27. JTS reserves the right to include Special Conditions in addition to the foregoing General Conditions if warranted by the particular circumstances of the required test or investigation [this clause is only effective when the other party has been informed.
28. The foregoing General Conditions shall in all respects be governed, construed, interpreted and operated in accordance with the relevant Chinese laws and regulations. Unless otherwise agreed, the arbitration shall take place in P.R.C.
29. These General Condition have been drafted in Chinese and may be translated into other languages. In the event of any discrepancy, the Chinese version shall prevail.
30. In general sample will be stored for 30 days. But for liquid, powder, etc semi-product & fragile product, it will be stored only for 15 days.
31. The data of project 10 is derived from the contract report numbered S22025091105-1E.

Zhejiang J-testing Service Co.,Ltd.

Add: West of 3/F, No.5 Building, No.968 Xuefeng West Road, Beiyuan Street, Yiwu, ZheJiang, China 322000  
Customer service: info@j-testing.com/+86 057985309611 Web: www.jts-cert.com